

COATED ELECTRODES

Oxford Alloy® 312-16

AWS E312-16 • Stainless Steel

Key Features

- ❖ Used to weld cast and wrought alloys of similar compositions.
- ❖ Also be used for joining hard to weld materials and dissimilar metals. Applications should be limited to 800°F (420°C). The weld deposits exhibit high tensile strength and offer some resistance to abrasion.

Conformances

AWS/ASME SFA 5.4
E312-16
UNS W31310

Chemical Composition - As required per AWS 5.4

C	Cr	Ni	Mn	Si	P	S
0.15 max	28.0-32.0	8.0-10.5	0.5-2.5	1.0 max	0.04 max	0.03 max
Mo	Cu					
0.75 max	0.75 max					

Mechanical Properties - As required by AWS 5.4

	Tensile Strength MPa (ksi)	Yield Strength MPa (ksi)	Elongation %
AWS Requirements	660 (95) min	Not specified	22 min
Typical Results - As welded	760 (110)	610 (88)	29



Typical Welding Parameters

Diameter		Process	Volt	Amps (flat)	Amps (V/OH)
in	(mm)				
3/32	(2.4)	SMAW	24-28	70-85	65-75
1/8	(3.2)	SMAW	26-30	85-110	80-90
5/32	(4.0)	SMAW	28-32	110-140	100-120
3/16	(4.8)	SMAW	28-32	120-160	110-130

Diameters & Packaging

Oxford Alloys USA			Oxford Alloys Asia Pacific		
Diameter (in)	Length (in)	Packaging (lbs)	Diameter (mm)	Length (mm)	Packaging (kgs)
3/32"	12	10 lb tube 30 lb carton	2.6	300	4 kg tube 12 kg carton
1/8"	14	10 lb tube 30 lb carton	3.2	350	5 kg tube 15 kg carton
5/32"	14	10 lb tube 30 lb carton	4.0	350	5 kg tube 15 kg carton
3/16"	14	10 lb tube 30 lb carton	5.0	350	5 kg tube 15 kg carton

Actual test results may vary. Refer test result disclaimer on page 160.